


RBW

Technical Data Sheet

SOILD WHITE BOTH SIDES HEAT SEALABLE, ONE SIDE CORONA TREATED
BOPP FILM

PROPERTIES

- Both sides heat sealable
- Excellent mechanical properties
- High opacity & bright whiteness
- Good slip & anti-static property
- Suitable for food contact



APPLICATIONS

- General overwrapping
- Printing (Rotogravure and Flexographic) & Lamination

Technical Properties	Units		Typical Values					Method	
Nominal Thickness	Micron		18	20	25	30	35	40	ROWAD
Unit Weight	gm/m ²		17.6	19.6	24.5	29.4	34.3	39.2	ROWAD
Yield	m ² /kg		56.8	51.02	40.8	34.0	29.2	25.5	ROWAD
Wetting Tension	dynes/cm		38min					ASTM D2578	
Transmission	%		40	38	35	30	28	26	ASTM D1003
Gloss @45°	%		>45					ASTM D2457	
C.O.F (FxF)			0.3					ASTM D1894	
Tensile Strength at Break	MD	N/mm ²	140					ASTM D882	
	TD	N/mm ²	240						
Elongation at Break	MD	%	160					ASTM D882	
	TD	%	60						
Heat Seal Strength	UT/UT	N/15mm	>2.3		>3.0			ROWAD 130°C 1 Bar, 1 Sec	
Dimensional Stability	MD	%	4.0					ROWAD 120°C, 5 Min/Air	
	TD	%	2.0						
Heat Seal Range (Un-Treated Side)	°C		105-140					ROWAD 1 Bar, 1 Sec	
Water Vapor Transmission Rate	gm/m ² /24hrs		4-6					ASTM F1249 38 °C,90% RH	

MD: Machine Direction, TD: Transverse Direction, FxF: UTR/UTR

STORAGE AND HANDLING

In order to minimize deterioration of the level of surface treatment, storage temperature of below 30 °C is recommended for Heat sealable both side treated films. The film should be conditioned at room temperature for at least 24 hours before use. RBW film is suitable for use up to 6 months from the date of production.

TREATMENT INDICATION

The film is normally supplied with outside corona treatment. Inside corona treated or both sides treated film can also be supplied if requested.

FOOD CONTACT

Raw Material used for production of the film is approved by EU and FDA. Specific document and safety data sheet are available on request.

For more information, please contact:

Rowad Global Packaging Company, P.O. Box 14164, Dammam 31424, Kingdom of Saudi Arabia | T: +966 3 8122204 | F: +966 3 8121360