



RBTH

Technical Data Sheet

TRANSPARENT FAST FILM, BOTH SIDES HEAT SEALABLE, ONE SIDE
CORONA TREATED, HOT SLIP BOPP FILM

PROPERTIES

- Both sides heat sealable
- Excellent mechanical properties
- High transparency and gloss
- Excellent hot slip & anti-static property
- Suitable for food contact

Treated Skin Layer

Core Layer

Hot Slip Seal Skin Layer

APPLICATIONS

- General overwrapping for fast packaging machines
- Card packaging

Technical Properties	Units		Typical Values		Method
Nominal Thickness	Micron		18	35	ROWAD
Unit Weight	gm/m ²		16.38	31.85	ROWAD
Yield	m ² /kg		61.05	31.40	ROWAD
Wetting Tension	dynes/cm		38 min		ASTM D2578
Haze	%		2.6		ASTM D1003
Gloss @45 °	%		85		ASTM D2457
C.O.F (FxF)			0.25		ASTM D1894
Tensile Strength at Break	MD	N/mm ²	140		ASTM D882
	TD	N/mm ²	260		
Elongation at Break	MD	%	180		ASTM D882
	TD	%	60		
Heat Seal Strength	UT/UT	N/15mm	>2.2	>4.0	ROWAD 130°C 1 Bar, 1 Sec
Dimensional Stability	MD	%	4.0		ROWAD 120°C, 5 Min/Air
	TD	%	2.0		
Heat Seal Range (Un-Treated Side)	°C		105-140		ROWAD 1 Bar, 1 Sec
Water Vapor Transmission Rate	gm/m ² /24hrs		4-8		ASTM F1249 38 °C,90% RH

MD: Machine Direction, TD: Transverse Direction, FxF: UTR/UTR

STORAGE AND HANDLING

In order to minimize deterioration of the level of surface treatment, storage temperature of below 30 °C is recommended for Heat sealable both side treated films. The film should be conditioned at room temperature for at least 24 hours before use. RBTH film is suitable for use up to 6 months from the date of production.

TREATMENT INDICATION

The film is normally supplied with outside corona treatment. Inside corona treated or both sides treated film can also be supplied if requested.

FOOD CONTACT

Raw Material used for production of the film is approved by EU and FDA. Specific document and safety data sheet are available on request.

For more information, please contact:

Rowad Global Packaging Company, P.O. Box 14164, Dammam 31424, Kingdom of Saudi Arabia | T: +966 3 8122204 | F: +966 3 8121360